

SHEERWEAVE®

Acoustical Test Data



SheerWeave Styles	NRC	SAA
BASIC 3%	0.60	0.60
BASIC 5%	0.10	0.08
2000	0.10	0.11
2100	0.05	0.06
2360	0.05	0.06
2390	0.10	0.12
2410	0.20	0.21
2500	0.55	0.54
2390 Performance +	0.15	0.14
2410 Performance +	0.25	0.23
2500 Performance +	0.50	0.49
2701	0.15	0.15
2703	0.10	0.09
2705	0.05	0.06
2710	0.05	0.05
4000 Ecolibrium	0.10	0.11
4100 Ecolibrium	0.05	0.05
4400 Ecolibrium	0.20	0.19
4500	0.15	0.17
4600	0.20	0.23
4550	0.10	0.11
4650	0.15	0.18
4800	0.30	0.31
4901	0.60	0.59
4903	0.25	0.25
5000	0.15	0.16
Infinity2 1%	0.20	0.23
Infinity2 3%	0.20	0.19
Infinity2 5%	0.10	0.11
7000	0.10	0.08
7100	0.05	0.03
7400	0.05	0.03
7450	0.25	0.25
7500	0.00	0.03
7500R	0.00	0.03
7600	0.05	0.07
7650	0.40	0.44
8000	0.20	0.22



Standard: ASTM C423-09a
Sound Absorption and Sound Absorption

Coefficients by the
Reverberation Room Method

NRC – Noise Reduction Coefficient
SAA – Sound Absorption Average